

Cyberbond Europe GmbH
Werner-von-Siemens-Str. 2
D – 31515 Wunstorf
Germany
Tel.: + 49 / 5031 / 95 66 – 0
FAX.: + 49 / 5031 / 95 66 – 26
E-mail: info@cyberbond.de
www.cyberbond.EU.com

TECHNICAL DATA SHEET

Cyberbond 2800

Profile:

Very fast Cyanoacrylate especially suitable for rubber bonding
USP Class VI approved

Physical Properties

A. Monomer Cyanoacrylate (fluid)

Monomer Base	Ethylester	
Appearance	colourless, clear	
Viscosity at 20°C	5	mPa*s
Density at 20°C	1,04	g / cm ³
Flashpoint	85	°C

Setting times on...

Plastic (ABS)	2	seconds
Elastomer (EPDM)	1	seconds
Wood (beech)	> 60	seconds
Storage stability*	12	months

B. Polymer Cyanoacrylate (solid)

Tensile strength on rubber (NBR)	# 64	N / cm ²
Tensile shear strength on steel	19,5	N / mm ²
Temperature range (Polymer)	-55 to +95	°C

#=material failure

*at room temperature in unopened original containers

The data mentioned in this data sheet, particularly the recommendations for application and use of products are based on our recent knowledge and experience. Due to the fact of having so many different materials involved and conditions of applications which are out of our influence, we strongly recommend to do sufficient tests in order to guarantee that Cyberbond products are suitable for the intended process and applications. Except for wilful acts any liability based on such recommendations or any verbal advice is hereby expressly excluded.

revised: January 2005